

WE92

Prepreg

Product Data Sheet

- High flow matrix
- Zero Volatile/Solvent Content
- Improved Health and Safety: Diuron-Free
- Long outlife at room temperature
- Available with a range of reinforcements
- Suitable for a range of pressures
- Low exothermic properties
- Controllable in thick sections
- Recommended cure between 85°C and 120°C
- Excellent laminate quality, low bleed

Introduction

WE92 is part of the WE and WT range of prepreg, SPRINT[®], and AIRSTREAM[™] products. This unique product range provides technically and commercially competitive engineering materials, ideal for use either solely, or in conjunction with other products from within the product range along with other Gurit products.

WE92 is a high flow, Diuron free epoxy prepreg ideally suited to the manufacture of thick sections. It can be cured at temperatures as low as 85°C, but can also be used for the rapid manufacture of components through its 35-minute cure at 120°C. All of this can be achieved together with an out-life of 60 days at 21°C.

WE92 is designed for vacuum bag processing and offers excellent mechanical performance on glass fibre reinforcements. Currently WE92 is pre-impregnated into E-glass fibres, which are manufactured as a triax, which is produced in large volumes in order to make it a cost-effective composite building block for a range of applications.

The triaxial prepreg is a $\pm 45^\circ$ biaxial E-glass stitched to unidirectional fabric giving a total fibre weight of either 900 or 1200g. This material can be used as a thick drapable fabric. The triaxial prepreg is available with a glass tissue on the biax side, which helps to prevent print-through.

Instructions for Use

WE92 Triax can be used with both SPRINT® or prepreg products. It is supplied with a poly backer and can be applied to the substrate with either side against the tool.

In order to maximise the potential of WE92 product range please contact the Gurit Technical Department. Contact details are on the back of this Product Data Sheet.

General prepreg working practices apply to these products, details of which can be obtained from the Guide to Composites or by contacting the above department.

Matrix Properties



Uncured

Thermal properties (20°C-250°C @ 10°C/minute)	
Enthalpy (J/g)	180

Time to 95°C - 95% Cure	
Minimum Cure Temperature (°C)	85
Time @ minimum cure temp (hours)	10
90°C (minutes)	300
100°C (minutes)	100
110°C (minutes)	60
120°C (minutes)	35

Colour	
Matrix	Translucent
Resin	Clear
Catalyst	White

Rheology		
	30-120°C @ 1°C/minute	30-120°C @ 2°C/minute
Temperature @ minimum Viscosity (°C)	102	111



Cured

Mechanical Properties	
Tensile Strength (MPa)	88
Tensile Modulus (GPa)	4
Tensile Strain (%)	4
Compression Strength (MPa)	144
Compression Modulus (GPa)	4
Matrix density (g/cm³)	1.2

Thermal properties (cured between 90°C-120°C)	
DSC T _g (°C)	110-135

Prepreg Properties

Uncured

Material Properties		
		Notes
Tack	4	Medium Tack

Outlife	
At -18°C (months)	18
At 5°C (months)	6
At 21°C (days)	60

Material Safety Information	
Hazard Code	Xi, N
Risk Phrases	36/38, 43, 51/53
Safety Phrases	24, 26, 28, 37/39, 57, 60
Solvent Content	0
Volatiles Content	0

Prepreg Reinforcements				
	900g	900g TEA50 Fleeced	1200g	1200g TEA50 Fleeced
Resin Content (%)	38	44	38	43
Fibre Weight (g/m ²)	900	950	1175	1225
Aerial Weight (g/m ²)	1452	1696	1895	2150
Stitch Type	Polyester	Polyester	Polyester	Polyester
Fleeced	No	Yes	No	Yes
Backer Type	100µm MDPE	100µm MDPE	100µm MDPE	100µm MDPE
Available Roll Length (m)	-	-	-	-
Available Roll Width (mm)	1260	1260	1260	1260
Packaging Type	PackagingType is dependant on the length of roll requested			

Cured

Prepreg Reinforcement					
	900g	900g Fleeced	1200g	1200g Fleeced	Test Method
0° Tensile Strength (MPa)	494	520	505	497	BS EN ISO 527
0° Tensile Modulus (GPa)	27	27	26	28	BS EN ISO 527
0° Tensile Strain to Failure (%)	1.6	1.5	2.0	1.8	BS EN ISO 527
0° Compressive Strength (MPa)	480	494	461	487	ISO 14126
0° Compressive Modulus (GPa)	28	274	28	28	ISO 14126
0° Compressive Strain to Failure (%)	1.4	1.6	1.5	1.4	ISO 14126
0° ILSS (MPa)	45	52	55	47	BS EN ISO 14130
45° Tensile Strength (MPa)	245	204	240	287	BS EN ISO 527
45° Tensile Modulus (GPa)	20	20	18	20	BS EN ISO 527
45° Tensile Strain to Failure (%)	1.0	0.72	1.3	1.4	BS EN ISO 527
45° ILSS (MPa)	35	30	36	33	BS EN ISO 14130

Health and Safety

The following points must be considered:

1. Skin contact must be avoided by wearing gloves. Gurit recommends the use of disposable nitrile gloves for most applications. The use of barrier creams is not recommended, but to preserve skin condition a moisturising cream should be used after washing.
2. If working in an enclosed area, local extraction and ventilation should be used.
3. Overalls or other protective clothing should be worn when laminating or sanding. Contaminated work clothes should be thoroughly cleaned before re-use.
4. Eye-protection should be worn. If contamination of the eyes occurs then flush the eye with water for 15 minutes, holding the eyelid open, and seek medical attention.
5. If the skin becomes contaminated then the area must be immediately cleansed. The use of resin-removing cleansers is recommended. To finish, wash with soap and warm water. The use of solvents on the skin to remove resins etc. must be avoided.

Washing should be part of routine practice:

- Before eating or drinking
- Before smoking
- Before using the lavatory
- After finishing work

6. The inhalation of sanding dust should be avoided. If it settles on the skin then it should be washed off. After more sanding operations, a shower/bath and hair wash is advised.

Gurit produces a separate full Material Safety Data Sheet (MSDS) for all hazardous products. Please ensure that you have the correct MSDS to hand for the materials you are using before commencing work. A more detailed guide for the safe use of Gurit resin systems is also available and can be found on our website at www.gurit.com. Note: safety datasheet legislation can vary with country of use.

CPDS are also available upon request

Applicable Risk & Safety Phrases

R 36/38, 43, 51/53

S 24, 26, 28, 37/39, 57, 60

Transport & Storage

All prepreg materials should be stored in a freezer when not in use to maximise their useable life, since the low temperature reduces the reaction of resin and catalyst to virtually zero. However, even at -18°C, the temperature of most freezers, some reaction will still occur. In most cases after some years, the material will become unworkable.

Notice

All advice, instruction or recommendation is given in good faith and the Company only warrants that advice in writing is given with reasonable skill and care. No further duty or responsibility is accepted by the Company. All advice is given subject to the terms and conditions of sale (the Conditions) which are available on request from the Company or may be viewed at the Company's website: www.gurit.com.

The Company strongly recommends that Customers make test panels and conduct appropriate testing of any goods or materials supplied by the Company to ensure that they are suitable for the Customer's planned application. Such testing should include testing under conditions as close as possible to those to which the final component may be subjected. The Company specifically excludes any warranty of fitness for purpose of the goods other than as set out in writing by the Company. The Company reserves the right to change specifications and prices without notice and Customers should satisfy themselves that information relied on by the Customer is that which is currently published by the Company on its website. Any queries may be addressed to the Technical Services Department.

The Company's data sheets are being continuously reviewed and updated. Please ensure that you have the current version before using the product, by contacting the SP Marketing Communications Department and quoting the revision number in the bottom left-hand corner of this page. Alternatively, the latest version can be downloaded from our web site: www.gurit.com

Gurit (UK) Ltd

St Cross Business Park
Newport, Isle of Wight
United Kingdom PO30 5WU

T +44 (0) 1983 828 000

F +44 (0) 1983 828 100

E info-uk@gurit.com

W www.gurit.com

Gurit (Australia) Pty Ltd

Unit 1A / 81 Bassett Street,
Mona Vale, 2103 NSW,
Australia

T +61 (0) 2 9979 7248

F +61 (0) 2 9979 6378

E sales-au@gurit.com

W www.gurit.com

Gurit (Canada) Inc

555 Boul. Poirier
Magog
QC J1X 7L1

T +1 819 847 2182

F +1 819 847 2572

E info-na@gurit.com

W www.gurit.com